

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
18 December 2003 (18.12.2003)

PCT

(10) International Publication Number
WO 03/103877 A1


- (51) International Patent Classification⁷: **B22D 1/00**
- (21) International Application Number: **PCT/BE03/00097**
- (22) International Filing Date: **3 June 2003 (03.06.2003)**
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data:
02447113.8 **7 June 2002 (07.06.2002) EP**
- (71) Applicant (for all designated States except US): **VESUVIUS CRUCIBLE COMPANY [US/US]**; Suite 200, 103 Foulk Road, Wilmington, DE 19803 (US).
- (71) Applicant (for ZM only): **VESUVIUS GROUP S.A. [BE/BE]**; 17, rue de Douvrain, B-7011 Ghlin (BE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **WILLOUGHBY, Craig [GB/GB]**; 82 Southgate, Eckington, Sheffield, S21 4FT (GB). **MILLWARD, Cavan [GB/GB]**; 12 Leigh Way, Hepthorne Lane, North Wingfield, Chesterfield, S42 5UA (GB).
- (74) Agent: **DEBLED, Thierry**; Vesuvius Group S.A., Intellectual Property Department, Rue de Douvrain 17, B-7011 Ghlin (BE).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

— as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI,

[Continued on next page]

(54) Title: INJECTION DEVICE AND PROCESS FOR THE INJECTION OF A FLUID



(57) Abstract: The invention relates to an injection device for the reliable introduction of a fluid into a metallurgical vessel having a refractory lining, the device being removably insertable in the lining; comprising a refractory first body (2) and a refractory second body (3) fittingly assembled, the first body (2) being made of a refractory material less permeable to the fluid than the material of the second body (3), the first and second bodies having each a surface (4, 5) adapted to contact molten metal; and having each fluid passages (6, 7) extending from fluid feeding means (8) to a surface (4, 5) adapted to contact molten metal, the relative flow resistance of the fluid passages (7) in the second body (4) being higher than that of the fluid passages (6) in the first body (2), the fluid passages (6) in the first body (2) being constituted of slots or bores. According to the invention, the fluid passages (6) in the first body (2) are independent from the fluid passages (7) in the second body (3). Such an injection device permits the reliable introduction of a fluid into a metallurgical vessel even when the injection device has already been used.



GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, *ARIPO patent* (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), *Eurasian patent* (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), *European patent* (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), *OAPI patent* (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,

MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, *ARIPO patent* (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), *Eurasian patent* (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), *European patent* (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), *OAPI patent* (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

INJECTION DEVICE AND PROCESS FOR THE INJECTION OF A FLUID.**Description.**

- 5 **[0001]** The present invention relates to injection devices for the introduction of a fluid into a metallurgical vessel and to a process for the injection of a fluid. In particular, the invention relates to such a device which is removably insertable in the lining of a metallurgical vessel.
- 10 **[0002]** Fluids, in particular gases, are often injected into molten metal in vessels such as ladles, crucibles or tundishes for diverse purposes. For instance, a gas may be introduced into the bottom part of a vessel to clear the relatively cool bottom area of solidification products, e.g. to remove them from the vicinity of a bottom pour outlet where the vessel has such an outlet. In steel making for example, the use of slow injection of a fine curtain of gas bubbles in the tundish assists in inclusion removal; the inclusions being attracted to the fine gas bubbles and rising upwards through the melt to the surface where they are conventionally captured by the tundish cover powder or flux. A fluid may also be introduced for rinsing or to homogenise the melt thermally or compositionally, or to assist in dispersing alloying additions throughout the melt.
- 15 **[0003]** Usually, an inert fluid is used but reactive fluids may also be employed, e.g. reducing or oxidising gases, when the melt compositions or components thereof needs modifying. For example, it is customary to inject gases such as nitrogen, chlorine, freon, sulphur hexafluoride, argon, and the like into molten metal, for example molten aluminium or aluminium alloys, in order to remove undesirable constituents such as hydrogen gas, non-metallic inclusions and alkali
- 20 metals. The reactive gases added to the molten metal chemically react with the undesired constituents to convert them into a form such as a precipitate, a dross or an insoluble gas compound that can be readily separated from the remainder of the melt. These fluids (or others) might also be used for example with steel, copper, iron, magnesium or alloys thereof.
- 25 **[0004]** Because of varied operational requirements, two different types of injection devices are employed:
- porous purging plugs, where the fluid streams through irregularly distributed and variously sized pores and
 - plugs where the fluid flow direction and also the size of the openings, through which the fluid is piped, are controlled. These openings can be round canals or bores, which are either kept
- 30 separate or interlinked or slots which, when segments are assembled, can be arranged in a straight line, or in a circle, by fitting two cone stumps together.
- 35 **[0005]** In order to achieve optimal cleaning, it is desirable that the fluid be introduced into the molten metal, preferably from the bottom of the recipient, in the form of a very large number of extremely small bubbles so as to quickly transport the non-metallic impurities or gases into the slag. As the size of gas bubbles decreases, the number of bubbles per unit volume increases. An increase in the number of bubbles and their surface area per unit volume increases the probability of the injected gas being utilised effectively to perform the expected cleaning or

rinsing operation. The best injection devices to achieve this cleaning or rinsing operation are therefore porous plugs.

[0006] Where homogenisation is necessary (i.e., where additives have to be distributed and dissolved) or a temperature balance has to be achieved, purging plugs are used to assist mixing
5 by blowing large amounts of gas into the metal bath. For these applications, purge plugs with directed porosity have proved to be the most effective alternative.

[0007] Generally, the choice of the injection device type will thus depend on the main requirements of a specific application.

[0008] As starting point for the present application, the inventors had in mind to improve the
10 reliability of the injection devices of the type "purge plugs with directed porosity". It is indeed generally considered that a constant flow of fluid through the directed porosity is necessary in order to prevent blockage by the ingress of molten metal. The need to shut-off the fluid supply at the end of each injection operation would therefore result in blockage and would tend to make difficult, if not impossible, the re-use of the injection device, especially if the available fluid
15 pressure is not sufficient to re-open the fluid passages. Generally, it is considered that below 10 bars there is a risk that injection devices of the type "purge plugs with directed porosity" could not open. To avoid that problem, Japanese patent application (Kokai) 60-46312 for example teaches to only use mass porosity to assist mixing.

[0009] European patent 424,502 already addresses this problem and proposes a gas injector
20 with gas passages formed as capillary bores or slots in a rod constituted of a gas impermeable refractory material. The capillary bores or slots are of such a small dimension that, in use, the molten metal is substantially unable to intrude into the passages.

[0010] Although this injection device already constitutes a great step forward in the reliability of fluid injection into a metallurgical vessel, it is desirable to find alternative injection devices.
25 Ideally, such injection device should at least equal the reliability of the gas injector disclosed in the European patent 424,402 and be produced economically and simply through conventional techniques and with conventional materials. It should also be possible to open this injection device even when the maximum available fluid pressure is relatively low (for example lower than 10 bars).

[0011] The German patent application DE-A1-1,101,825 discloses an injection device for the
30 introduction of a fluid into a metallurgical vessel having a refractory lining, the device

- being removably insertable in the lining;
- comprising a refractory first body and a refractory second body fittingly assembled, the first and second bodies having each a surface adapted to contact molten metal; and
- 35 - having fluid passages extending from fluid feeding means to a surface adapted to contact molten metal and comprising fluid passages in the first body and in the second body, the relative flow resistance of the fluid passages of the second body being higher than that of the fluid passages of the first body.

[0012] According to the invention, the fluid passages in the first body are independent from the

fluid passages in the second body. It has indeed been observed that when the directed porosity of the first body is interlinked with the fluid passages of the second body as disclosed in DE-A1-1,101,825 - for example when slots of the first body are directly adjacent to the second body - this could result in the separation of the bodies. In particular, when one of the bodies is inserted
5 in another body, this results in a blow out of the surrounded body.

[0013] According to the invention, the fluid passages of the first body - which have thus generally wider openings - are more prone to blockage after shut-off of the fluid supply. When the fluid pressure is applied to the injection device, the fluid will therefore be first introduced into the molten metal through the second body if the injection device has already been used and
10 some metal remains on its surface blocking the fluid passages of the first body. As the pressure increases progressively, the flow rate through the second body increases until the fluid plume will begin to impact on the molten metal contact surface of the first body through a phenomenon of back attack fluid flow which causes molten metal agitation.

[0014] Eventually, this attack of the molten metal contact surface of the first body will result in
15 the clearance and opening of the first body fluid passages. The relative flow resistance of the fluid passages of the second body being higher than that of the fluid passages of the first body, the fluid will tend to follow the path of least resistance and therefore will flow through the fluid passages of the first body while the second body will substantially cease to allow fluid passage. This will allow a higher flow rate to pass within the molten metal, with all the above listed advantages of the purge
20 plug with directed porosity.

[0015] Preferably, the fluid feeding means for the fluid passages of the first and second bodies are common.

[0016] According to a preferred embodiment of the invention, the fluid passages of the first and second bodies are formed differently so that the relative flow resistances of these fluid passages
25 can be appropriately controlled. Advantageously, the second body is constituted of a fluid permeable refractory material, i.e. a material which is porous to the said fluid in the conditions of use. Advantageously, the second body is made of a pressed refractory material whose granulometry is defined so as to achieve the desired porosity.

[0017] The inventors have indeed observed that the second body made of a refractory material
30 which is permeable to the fluid to inject is far less sensitive to molten metal penetration than the fluid passages in the first body and that, consequently, during initial flowing of the fluid, the fluid passages constituted by the porous arrangement of the second body clears and opens more readily than the fluid passages in the first body. In other words, a lower pressure is necessary to clear and open the fluid passages in the second body.

[0018] A further advantage which has been unexpectedly observed with this preferred
35 embodiment is the following: when the metal penetration in the fluid passages of the first body is too severe so that these fluid passages fail to open directly under the effect of the back attack fluid flow streaming from the fluid permeable second body, then, for a certain time, all the fluid is injected through the second body. This results in the surface of the second body wearing to

some extent. When the second body has worn back to below the level of the surface of the first body. This results in turn to a surface layer of the first body above the remaining surface of the second body becoming weaker and breaking away easier. Eventually, the blocked surface of the first body having broken away, the fluid passages of the first body are cleared and can now open easily. It is believed that this results from the fact that a fluid permeable refractory material is more prone to wear.

[0019] Numerous arrangements of the first and second bodies in the injection device can be considered. For example, the second body can be formed as an annular porous ring surrounding a first body comprising slots formed in a fluid-impermeable material. However, the above discussed advantage is particularly noticeable when the second body is fittingly inserted in the first body, preferably in the middle of the first body so that the wear pattern of the molten metal contacting surface of the injection device is more even across this surface. In an advantageous embodiment of the invention, the fluid passages in the first body are aligned radially from the centre point of the second body so that all the fluid passages of the first body will be affected equally by the surface wear resulting from the fluid streaming from the second body. Nevertheless, for constructional and economical reasons, it can be advantageous to maximize the dimension of the second body. Therefore, the invention also relates to an injection device wherein the fluid passages in the first body are arranged substantially parallel to the interface between the first and second bodies so that the second body can occupy more space. The second body can have a round or polygonal section.

[0020] In a preferred variant of the invention, the first body is made of a refractory material less permeable to the fluid than the material of the second body, for example of a castable material, and the fluid passages extending therethrough are constituted of slots or bores, preferably of controlled direction and opening sizes.

[0021] In another of its aspects, the invention relates to a process for the reliable injection of a fluid into a metallurgical vessel comprising the steps of

- a) feeding an injection device with the fluid to introduce into the metallurgical vessel;
- b) injecting the said fluid through a initiating section of the injection device having higher fluid flow resistance than the remainder of the injection device (the initiating section being able to open more easily than the remaining sections of the injection device);
- c) using the fluid flow streaming from the said initiating section for cleaning and opening fluid passages in an injection section of the injection device having less fluid flow resistance than the initiating section;
- d) injecting the fluid into the metallurgical vessel through the injection section while the initiating section substantially ceases to allow fluid passage.

[0022] The invention will now be better described with reference to the enclosed drawings which are only provided for the purpose of illustrating the invention and not to limit its scope. Fig. 1 shows schematically an injection device according to the invention and Fig. 2 is a top view of the injection device shown at Fig. 1. Fig. 3 is a top view of a variant of the injection device.

[0023] In these figures, the injection device (1) is inserted into the lining of a metallurgical vessel (not shown) with its molten metal contacting surfaces (4, 5) at least level with the surface of the lining. The injection device is comprised of at least first and second bodies (2, 3) which are fittingly assembled. Most often the injection device is enveloped in a metal can (9). The first
5 body (2) comprises fluid passages (6) – constituted by slots - extending from fluid supply means (8) to its molten metal contacting surface (4). The second body (3) comprises fluid passages (7) – constituted by the porosity of the material - extending from its molten metal contacting surface (5) to fluid supply means (8). In the embodiment of figure 2, the fluid passages 6 extend radially from a centre point of the second body. In the embodiment of figure 3, the fluid passages 6 are
10 arranged substantially parallel to the interface between the first and second bodies (2,3). In the embodiment depicted on Figs. 1 to 3, the fluid supply means (8) are constituted by a plenum chamber which is connected to a fluid feeding pipe (not shown).

It has been observed that a fluid pressure of 6 to 9 bars is sufficient to open the fluid passages of the injection device according to the invention.

Claims.


1. Injection device (1) for the introduction of a fluid into a metallurgical vessel having a refractory lining, the device
5 - being removably insertable in the lining;
 - comprising a refractory first body (2) and a refractory second body (3) fittingly assembled, the first body (2) being made of a refractory material less permeable to the fluid than the material of the second body (3),
 the first and second bodies
10 - having each a surface (4, 5) adapted to contact molten metal; and
 - having each fluid passages (6, 7) extending from fluid feeding means (8) to a surface (4, 5) adapted to contact molten metal,
 the relative flow resistance of the fluid passages (7) in the second body (3) being higher than that of the fluid passages (6) in the first body (2), the fluid passages (6) in the first body (2)
15 being constituted of slots or bores, **characterised in that** the fluid passages (6) in the first body (2) are independent from the fluid passages (7) in the second body (3).
2. Injection device according to claim 1, **characterised in that** the second body (3) is fittingly inserted in the first body (2).
3. Injection device according to claim 2, **characterised in that** the second body (3) is inserted in
20 the middle of the first body (2).
4. Injection device according to claim 3, **characterised in that** the fluid passages (6) in the first body are substantially parallel to the interface between the first and second bodies (2,3).
5. Injection device according to claim 3, **characterised in that** the fluid passages (6) in the first body are aligned radially from the centre point of the second body (3).
- 25 6. Injection device according to claim 1, **characterised in that** the second body is made of a refractory material permeable to the said fluid.
7. Injection device according to claims 6, **characterised in that** the second body is made of a pressed refractory material.
8. Injection device according to claim 1, **characterised in that** the slots or bores are of controlled
30 direction and opening sizes.
9. Injection device according to claim 1, **characterised in that** the first body is made from a castable material.
10. Process for the injection of a fluid into a metallurgical vessel comprising the steps of
 a) feeding an injection device (1) with the fluid to introduce into the metallurgical vessel;
35 b) injecting the said fluid through a initiating section (3) of the injection device (1) having

higher fluid flow resistance than the remainder of the injection device;

c) using the fluid flow streaming from the said initiating section (3) for cleaning and opening fluid passages (6) in an injection section (2) of the injection device having less fluid flow resistance than the initiating section;

5 d) injecting the fluid into the metallurgical vessel through the injection section (2) while the initiating section (3) substantially ceases to allow fluid passage.

1/1



INTERNATIONAL SEARCH REPORT

PCT/BE 03/00097

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 B22D1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 B22D C21C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

PAJ, EPO-Internal, WPI Data, COMPENDEX

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 101 825 A (VEITSCH RADEX GMBH) 23 May 2001 (2001-05-23)	10
A	abstract paragraph '0007! - paragraph '0012! paragraph '0022! - paragraph '0029! paragraph '0034!; claims 1-9; figures 1,2	8
A	PATENT ABSTRACTS OF JAPAN vol. 2002, no. 09, 4 September 2002 (2002-09-04) & JP 2002 129224 A (SHINAGAWA REFRACT CO LTD), 9 May 2002 (2002-05-09) abstract figures 1-3	1-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

28 August 2003

Date of mailing of the international search report

05/09/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Ceulemans, J

INTERNATIONAL SEARCH REPORT

PCT/BE 85/00097

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 009, no. 175 (C-292), 19 July 1985 (1985-07-19) -& JP 60 046312 A (HARIMA TAIKA RENG K), 13 March 1985 (1985-03-13) abstract	1-10
A	US 5 573 724 A (SOOFI MADJID ET AL) 12 November 1996 (1996-11-12) the whole document	1-10

INTERNATIONAL SEARCH REPORT

PCT/BE 03/00097

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1101825	A	23-05-2001	DE 19954918 A1 AT 245202 T DE 50002898 D1 EP 1101825 A1	31-05-2001 15-08-2003 21-08-2003 23-05-2001
JP 2002129224	A	09-05-2002	NONE	
JP 60046312 4	A		NONE	
US 5573724	A	12-11-1996	NONE	